

PLASTI DIP®

MULTI-PURPOSE RUBBER COATING

DESCRIPTION:

PLASTI DIP® is an air dry, synthetic rubber coating that can be easily applied by spraying, brushing or dipping. PLASTI DIP® resists moisture, acids, abrasion, weathering, electrical shock, skidding/slipping, corrosion; coats and gives a comfortable, controlled, color coded grip to all types of tools; lawn and garden, mechanical, electrical, woodworking and masonry. PLASTI DIP® can also be applied to:

Wood: seals and protects from weathering and prevents splinters.

Metal: reduces vibration, deadens sound, prevents corrosion, insulates electrically and from extreme temperatures.

Glass: shatterproofs glass objects (available in clear).

Rope/Fabrics: weatherproofs, prevents rotting and fraying.

Plastics: protects delicate surfaces from scratches.

Rubber: weatherproofs, wear resistant.

Maps: weatherproofs, tear resistant (available in clear).

SPECIFICATIONS:

Solids: (wt.) 24%

Tensile: (ASTM D -638) 3,740psi

Elongation: (ASTM D -638) 430%

Cut resistance: (ASTM D -1044) very good

Stone abrasion: (ASTM D -3170) excellent

Shelf life: 1 year at 77°F

Chemical resistance:

acids, alkalines, pollutants: excellent

petroleum: limited

Durometer: shore A (ASTM D -2240) 70

Salt spray: (ASTM B -117) passed 1,000 hours

Weatherability: (ASTM G -53) 3-5 years: PLASTI DIP

7 - 10 years: PLASTI DIP U.V. Stable

Temperature use range: -30°F to 200°F.

Viscosity range: 80 – 100 K.U. @ 77 °F (+/- 2°F)

Permeability: (ASTM E -96) .03 grains/sq. ft./hr.

Coverage: 30 sq.ft. per gallon at 15 mils

Dielectric: (ASTM D -149) 1,400 v/mil

ALTERNATIVE PRODUCTS:

For a water base alternative see HCFeccs® technical data sheet

SURFACE PREPARATION:

MIX WELL BEFORE USE.

All surfaces to be coated must be free of all oils, grease, dirt, wax and loose rust. A sandblasted or rough surface improves adhesion. Use PLASTI DIP® PRIMER on all metals for best results.

USE ADEQUATE VENTILATION.



Unit 1 Harvesting Lane
East Meon
Petersfield
Hampshire
GU32 1QR

SPRAYING: Pressure pot may be used (siphon cup not recommended). Dilute with recommended thinners up to 50% as needed. Gently mix before spraying. Apply wet overlapping coats, holding gun 6" -12" from surface, using a 4"-6" pattern. Allow 10 -20 minutes dry time before applying additional coats to desired thickness.

RECOMMENDED EQUIPMENT AND SETTINGS:

Gun: Binks® model 95
Nozzle: 63B
Needle: 663A
Material: 20-25psi
Atomization: 15-25psi
Dilution: as needed
Cap: 63PB (up to 50% dilution) or 66S D (up to 50% dilution) for heavier build up.
Clean up: see recommended thinners.

SPRAYING: Airless equipment may be used. Use as described above.

Tip size: .011 - .019
Pressure: as needed
Dilution: up to 50%

DIPPING: Dilute with recommended thinners up to 25% as needed. Gently mix before each use. Do not introduce air bubbles. Insert item 1" every 5 seconds. Remove at same rate. Allow 30 -40 minutes (dry to the touch) dry time before applying additional coats to desired thickness.

BRUSHING: Dilute with recommended thinners up to 25% as needed. Gently mix before each use. Apply wet overlapping coats using a soft natural bristle brush. Allow 10 -20 minutes (dry to the touch) dry time before applying additional coats to desired thickness.

HINTS:

Recommended thinners: PLASTI DIP ® THINNER, Toluene or VM&P Naphtha. A dry film thickness of 12 -15 mils is recommended for best results. Approximate dry mil thickness per coat, dipping 6 -8 mils; brushing 4 -5 mils; spraying 2-5 mils. **Allow 4 hours dry time per coat before use.** Allow overnight drying whenever possible. When using a dip tank, allow 6" minimum from fluid surface to tank top to avoid "skinning over". Avoid excessive air movement, heat or humidity. Always use proper ventilation and protection.

ADDITIONAL APPLICATION IDEAS

Transformers	Cables / Straps
Rope	Wood
Joy Sticks	Circuit Boards
Electrical Boxes placed on the ground	Magnets
Stove/Oven handles	Fabric
LaCrosse Sticks/Nets	Astro Turf
Food Grade Barrels	Crutch Handles
Control Boxes	Relay Electric Wench
Metal Grates	Sharp edges
Pumps	Hand Tools
Valves / Actuators	Curtains
Pulleys & Rings	Clips
Poles	Glass
Underground tanks	Pipes
Hardware & Metal surfaces to prevent electrical discharge & sparks	

We cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the applications of this information or the safety and suitability of our products, either alone or in combination with other product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products whether used alone or in combination with other products. Ever changing V.O.C. regulations in your area may require you to contact local authorities for proper use and/or disposal of this product. Should you need further assistance, please contact PLASTI DIP INTERNATIONAL technical service.

PLASTI DIP, HCF, Performix and logo are registered trademarks of PLASTI DIP INTERNATIONAL
BINKS is a registered trademark of BINKS MFG. CO., Franklin Park, IL