



Textiles F.R. Limited incorporating **Perrotts**
Flame Retardancy Finishers & Consultants

Unit 4B, (30) Wharfedale Road
 Euroway Trading Estate
 Bradford
 West Yorkshire
 BD4 6SG

Tel: 01274 651230
 Fax: 01274 651305
 E-mail: sales@textilesfr.co.uk
 Web site: www.textilesfr.co.uk



Test Report & Certificate

UKAS TESTING LABORATORY No.1413

British Standard Flammability Test Document: 13377 Page 1 of 1

Test Method : BS5438:1976:Test 2

Specification: BS5867:Part 2:1980:Type B Contract Curtain Test

Order Details

TFR Order No : 172850
 Customer Order : GARY
 Order Date : 10/10/2008
 Fabric Description : BLACK WOOL
 Fabric Composition :
 Quantity (metres) : 1.0

Sample Conditioning : Test specimens were maintained for at least 72 hours at indoor ambient temperature & humidity prior to introduction to the conditioning room for 16 hours with an environment of 20°C +/- 5°C and Relative Humidity 60% +/- 5 %

Test Enclosure Conditions : Temperature 21 °C Relative Humidity 59 %

Cleansing Procedure : None Specified

Other Details :

Sample Treatment : Sample tested in an as received state

Test Procedure:
 Six specimens were prepared each measuring 220mm x 170mm, three with the longer dimension in the length and three with the longer dimension in the width. A butane flame was applied to the sample face for 15 seconds.

Report Notes:
 This test was carried out in accordance with BS5438, test method 2. The results may not apply to situations where there is a restricted air supply or prolonged exposure to large sources of heat such as in a conflagration.

OBSERVATIONS

OBSERVATIONS	Warp Direction			Weft Direction		
	Rep1	Rep2	Rep3	Rep1	Rep2	Rep3
Flame reached an edge	No	No	No	No	No	No
Hole reached an edge	No	No	No	No	No	No
Flaming debris	No	No	No	No	No	No

Comments:

COMPLIANCE REQUIREMENTS: No part of any hole nor any part of the lowest boundary of any flame shall reach the upper edge or either vertical edge of any specimen and there shall be no separation of flaming debris from any specimen.

The sample complied with the requirements for BS5867:Part 2:1980:Type B

Conducted by : Mr.P. TAYLOR
 Laboratory Technician
 Authorised by: Miss K. BUTTON
 Office Manager

Date 15/10/2008

Date 15/10/2008