



## TECHNICAL DATA SHEET

### PRODUCT: POLYVINE FROSTING VARNISH

#### PRODUCT DESCRIPTION

Developed to reproduce the unique visual effect of etched glass. This acrylic medium is used with stencils to transform plain glass panels into classic or modern designs.

#### APPLICATION

First ensure that the glass is perfectly clean and free from grease, and is not cold, since any condensation or moisture will spoil the result. Apply a cut stencil pattern with Polyvine Stencil Tack, or cover the glass with masking tape and cut out a design of your own, peeling away the cutout.

Brush a light coat of Frosting Varnish evenly onto the glass and produce the texture using a small dry sponge roller. Carefully remove the stencil or masking tape before the varnish dries. When cleaning the glass, use warm soapy water - do NOT use solvent-based window-cleaning agents. Can be tinted with Polyvine Colourisers.

#### COVERAGE

Approx. 8 sq. m per litre.

#### CLEAN UP

Any equipment used can be cleaned using soap and water before the clear coat dries. Wipe any excess off surfaces with a damp cloth. Any dried deposits will need a paint stripper to remove them.

#### FILM PROPERTIES

DRY FILM: Satin

DRYING TIME: approx. 30 minutes @ 20°C / 70°F

RECOAT TIME: 1-2 hours

CURE TIME: approx 5 days @ 20°C / 70°F

HARDNESS: approx. 150 sec Konig hardness

NON YELLOWING

RESISTANT TO: Water, tea, coffee, detergent.

#### PACKAGING

500ml.

**STORAGE**

Store in unopened containers in a cool dry place away from direct sunlight.

**HEALTH SAFETY AND THE ENVIROMENT**

Non-hazardous. Ensure good ventilation. Keep out of reach of children. Contact with eyes-wash immediately with warm water. Remove excess from tools and mixing vessels before washing in warm soapy water. Do not empty containers into drains or watercourses.

The information supplied herein is accurate to the best of our knowledge. Since conditions and methods are beyond our control, no warranty is expressed or implied. You are advised to access the suitability of the product on a test area before application

Further information may be obtained from:

**POLYVINE LIMITED**

Vine House  
Cheddar Business Park  
Wedmore Rd.  
Cheddar BS27 3EB  
United Kingdom

Telephone No. 0845 017 1671  
International +44 845 017 1671  
Fax: 0845 017 1672  
Email [info@polyvine.co.uk](mailto:info@polyvine.co.uk)

Date of issue: August 2015